




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : G11B	A2	(11) International Publication Number: WO 99/59143 (43) International Publication Date: 18 November 1999 (18.11.99)
<p>(21) International Application Number: PCT/IB99/00840</p> <p>(22) International Filing Date: 10 May 1999 (10.05.99)</p> <p>(30) Priority Data: 98201552.1 12 May 1998 (12.05.98) EP</p> <p>(71) Applicant: KONINKLIJKE PHILIPS ELECTRONICS N.V. [NL/NL]; Groenewoudseweg 1, NL-5621 BA Eindhoven (NL).</p> <p>(71) Applicant (for SE only): PHILIPS AB [SE/SE]; Kottbygatan 7, Kista, S-164 85 Stockholm (SE).</p> <p>(72) Inventors: WIERENGA, Harm, A.; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). RIJERS, Johannes, C., N.; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).</p> <p>(74) Agent: STOLK, Steven, A.; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).</p>		<p>(81) Designated States: JP, KR, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>Without international search report and to be republished upon receipt of that report.</i></p>
<p>(54) Title: REWRITABLE OPTICAL INFORMATION MEDIUM</p> <p>(57) Abstract</p> <p>A description is given of a rewritable single-sided double layer optical information medium having a first recording stack (2) with a phase change recording layer (4) sandwiched between two dielectric layers (3, 5). The recording stack (2) is sufficiently transmissive to ensure proper reading/writing of the second recording stack (9). For this purpose, the recording stack (2) comprises a thin metal layer (6) and a further dielectric layer (7). The laser beam (14, 15) can be focused on the first recording stack (2) or on the second recording stack (9), thus doubling the storage capacity of the recording medium.</p>  <p>The diagram illustrates a cross-section of a rewritable optical information medium. It shows two recording stacks, labeled 2 and 9. The first recording stack (2) is composed of layers 3, 4, 5, 6, and 7. Layer 4 is a phase change recording layer sandwiched between dielectric layers 3 and 5. Layer 6 is a thin metal layer, and layer 7 is a further dielectric layer. The second recording stack (9) is composed of layers 10, 11, 12, and 13. Two laser beams, labeled 14 and 15, are shown focusing on the first and second recording stacks respectively. The medium is shown as a single-sided double layer.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Rewritable optical information medium.

The invention relates to an optical information medium for rewritable double layer recording by means of a laser-light beam, said medium comprising a substrate having disposed on the same side thereof two recording stacks both having a phase change type recording layer.

5 Optical information or data storage based on the phase change principle is attractive, because it combines the possibilities of direct overwrite (DOW) and high storage density with easy compatibility with read-only systems. Phase-change optical recording involves the formation of submicrometer-sized amorphous recording marks in a thin crystalline film using a focused laser-light beam. During recording information, the medium is
10 moved with respect to the focused laser-light beam which is modulated in accordance with the information to be recorded. Due to this, quenching takes place in the phase-change recording layer and causes the formation of amorphous information bits in the exposed areas of the recording layer which remains crystalline in the unexposed areas. Erasure of written amorphous marks is realized by recrystallizing through heating with the same laser. The
15 amorphous marks represent the data bits, which can be reproduced via the substrate by a low-power focused laser-light beam. Reflection differences of the amorphous marks with respect to the crystalline recording layer bring about a modulated laser-light beam which is subsequently converted by a detector into a modulated photocurrent in accordance with the coded, recorded digital information.

20 One of the aims in optical recording is to increase the storage capacity of media like DVD-Rewritable and DVR (Digital Video Recorder) on a single-sided disc. This can be achieved by reducing the laser wavelength λ , and/or increasing the numerical aperture (NA), because the laser spot size is proportional to $(\lambda / \text{NA})^2$. An alternative option is the application of multiple recording layers. When two recording layers on the same side of the optical disc
25 are used, this is called double or dual layer recording.

An optical information medium of the phase change type having a single recording layer is known from the international patent application WO 97/50084 (PHN 15881)

filed by Applicants. The known medium of the phase change type comprises a substrate carrying a stack of layers comprising a first dielectric layer of e.g. $(\text{ZnS})_{80}(\text{SiO}_2)_{20}$, a phase change recording layer of a GeSbTe compound, a second dielectric layer, and a reflective metal mirror layer. Such a stack of layers can be referred to as an IPIM structure, wherein M represents a reflective or mirror layer, I represents a dielectric layer, and P represents a phase change recording layer. The metal layer serves not only as a reflective mirror, but also as a heat-sink to ensure rapid cooling for quenching the amorphous phase during writing. The known recording medium has a good cyclability, i.e. a large number of repeated writing and erasing operations are possible, is suitable for high speed recording, and shows a low jitter even after a large number of cycles. In said patent application, double layer recording is not disclosed.

For double layer recording, the first or upper recording stack must be sufficiently transmissive to ensure proper read/write characteristics of the second or lower recording stack. However, the known IPIM structure for rewritable phase change recording has a crystalline absorption of about 80% and a crystalline reflection of about 20%, thus ensuring a high temperature increase in the phase change recording layer, a high modulation, and proper tracking, with limited laser power. Since the IPIM structure is not transmissive, it is unsuitable as a first or upper recording stack, although it has a proper structure for the second or lower recording stack, where zero transmission is preferable. A possible solution could be the replacement of the mirror layer M by a transparent heat conductor such as aluminium nitride. However, the thermal conductivity of these materials in thin films still appears to be too low, and therefore their ability to rapidly reduce the temperature in the recording layer is insufficient.

25

It is an object of the invention to provide, *inter alia*, a single-sided rewritable double layer optical information medium having recording stacks with an IPIM structure, in which the storage capacity is doubled with respect to a single-layered information medium.

This object is achieved in accordance with the invention by an optical information medium as described in the opening paragraph, which comprises, in this order:

- a first recording stack comprising a phase change type recording layer sandwiched between two dielectric layers, and a transparent metal layer and a further dielectric layer on the side opposite the side of the first recording stack on which the laser-light beam is incident;

30

- a transparent spacer layer having a thickness larger than the depth of focus of the laser-light beam; and
- a second recording stack comprising a phase change type recording layer sandwiched between two dielectric layers, and a metal mirror layer on the side opposite the side of the second recording stack on which the laser-light beam is incident.

The optical information medium according to the invention has the following structure:

substrate | IPIMT⁺ | S | IPIM

wherein the IPIMT⁺ stack is the first recording stack with the further dielectric layer I⁺, S is a transparent spacer layer, IPIM is the second recording stack, and wherein I, P, and M have the above mentioned meaning. The laser-light beam is incident *via* the substrate.

The invention is based on the insight that the transmission of an IPIM stack is increased when the metal layer M is replaced by a thin metal film, which is transparent for the laser-light beam, in combination with a further dielectric layer. For example, the transmission of a recording stack with a 10 nm thick Ag layer can be increased by about 50% by the addition of a further dielectric layer, without adversely affecting the optical contrast between the amorphous and crystalline phase. For this reason the laser power for writing in the second recording stack can be reduced by about 50%.

The metal layer of the first recording stack is thin, i.e. it has a thickness between 10 and 30 nm. This thickness is sufficient for quenching the amorphous phase during writing, and allows sufficient transmission to ensure proper read/write characteristics of the second recording stack. The metal may be selected from Al, Cu, or Au, but is preferably made of Ag, because of its high transmissivity and good thermal conductivity.

The dielectric layers are preferably made of a mixture of ZnS and SiO₂, e.g. (ZnS)₈₀(SiO₂)₂₀. The layers may also be made of SiO₂, Ta₂O₅, TiO₂, ZnS, Si₃N₄, AlN, Al₂O₃, MgO, ZnO, SiC, including their non-stoichiometric compositions. Especially the last six members are preferred because of their good thermal conductivity.

For the metal mirror layer of the second recording stack, metals such as Al, Ti, Au, Ni, Cu, Ag, Rh, Pt, Pd, Ni, Co, Mn and Cr, and alloys of these metals, can be used. Examples of suitable alloys are AlTi, AlCr and AlTa. The thickness of this metal mirror layer is not critical, but preferably the transmission is zero for obtaining maximal reflection. For practical reasons the thickness is about 100 nm.

The recording layer comprises a phase change material showing a crystalline-amorphous phase transition. Known materials are e.g. alloys of In-Se, In-Se-Sb, In-Sb-Te, Te-

Ge, Te-Se-Sb, Te-Ge-Se, or Ag-In-Sb-Te. Preferably, the recording layer comprises a GeSbTe compound. Especially useful are the compounds described in the above mentioned international patent application WO 97/50084. These compounds have a composition defined in atomic percentages by the formula:

- 5 $\text{Ge}_{50x}\text{Sb}_{40-40x}\text{Te}_{60-10x}$, wherein $0.166 \leq x \leq 0.444$. These compositions are situated on the line connecting the compounds GeTe and Sb_2Te_3 in the triangular Ge-Sb-Te composition diagram, and include the stoichiometric compounds $\text{Ge}_2\text{Sb}_2\text{Te}_5$ ($x=0.445$), GeSb_2Te_4 ($x=0.286$) and GeSb_4Te_7 ($x=0.166$). These compounds show a fast crystallization (erasure) time.

- 10 Preferably, the recording layer of the first recording stack has a thickness between 5 and 15 nm. A thicker layer would result in too low a transmission. The recording layer of the second recording stack may be thicker, e.g. between 5 and 35 nm.

- 15 In the first recording stack, the dielectric layer between the substrate and the phase change recording layer protects the recording layer from humidity, the substrate from thermal damage, and optimises the optical contrast. From the viewpoint of jitter, the thickness of this dielectric layer is preferably at least 70 nm. In view of optical contrast, the thickness of this layer is limited to $(70 + \lambda / 2n)$ nm, wherein λ is the wavelength of the laser-light beam, and n is the refractive index of the dielectric layer. In the second recording stack, the dielectric layer between the spacer layer and the recording layer has a thickness within the same range for the same reasons.

- 20 In both recording stacks, the dielectric layer between the recording layer and the metal (mirror) layer is between 10 and 50 nm, preferably between 20 and 40 nm. When this layer is too thin, the thermal insulation between the recording layer and the metal mirror layer is adversely affected. As a result, the cooling rate of the recording layer is increased, which leads to a poor crystallization process and a poor cyclability. The cooling rate will be
25 decreased by increasing the thickness of the second dielectric layer.

The further dielectric layer of the first recording stack is optimized for a maximum transmission, and depends on the refractive index n of the dielectric material. E.g. when $n=2$ the thickness is about 60 nm, whereas for $n=3$ the thickness is about 32 nm.

- 30 The transparent spacer layer between the first and second recording stack has a thickness larger than the depth of focus of the laser-light beam, e.g. $10 \mu\text{m}$. This thickness ensures that the first and second recording stacks are optically decoupled, i.e. a laser-light beam focused on the (recording layer of the) first recording stack does not read/write information from/onto the second recording stack, and *vice versa*. In this way the storage capacity is doubled with respect to a single-layered information medium. The material of the

spacer layer is e.g. a UV-cured acrylate adhesive, in which servotracks may be provided by a replication process.

The substrate of the information medium is at least transparent for the laser wavelength, and is made, for example, of polycarbonate, polymethyl methacrylate (PMMA),
5 amorphous polyolefin or glass. In a typical example, the substrate is disc-shaped and has a diameter of 120 mm and a thickness of 0.6 or 1.2 mm. The laser-light beam enters the stack via the entrance face of the substrate.

The surface of the disc-shaped substrate on the side of the recording layer is, preferably, provided with a servotrack which can be scanned optically. This servotrack is often
10 constituted by a spiral-shaped groove and is formed in the substrate by means of a mould during injection moulding or pressing. These grooves can be alternatively formed in a replication process in the synthetic resin of the spacer layer, for example, a UV light-curable acrylate

Optionally, the outermost layer of the stack is screened from the environment
15 by means of a protective layer of, for example, UV light-cured poly(meth)acrylate.

Recording and erasing can be achieved by using a short-wavelength laser, e.g. with a wavelength of 660 nm or shorter (red to blue).

Both the metal mirror layer, and the dielectric layers can be provided by vapour deposition or sputtering.

20 The phase change recording layer can be applied to the substrate by vacuum deposition, electron beam vacuum deposition, chemical vapour deposition, ion plating or sputtering.

25 The invention will be elucidated in greater detail by means of an exemplary embodiment and with reference to the accompanying drawing, in which the Figure shows a schematic cross-sectional view of an optical double layer information medium in accordance with the invention.

30 Exemplary embodiment.

The Figure schematically shows a part of a cross-section of a double layer optical information disc in accordance with the invention. The dimensions are not drawn to scale. Reference numeral 1 denotes a polycarbonate disc-shaped substrate having a diameter of 120 mm and a thickness of 0.6 mm. The substrate 1 is provided with:

a first recording stack 2 with a IPIM⁺ structure comprising:

- a dielectric layer 3 of $(\text{ZnS})_{80}(\text{SiO}_2)_{20}$ with a thickness of 190 nm,
- a recording layer 4 of the compound GeSb_2Te_4 with a thickness of 6 nm,
- a dielectric layer 5 of $(\text{ZnS})_{80}(\text{SiO}_2)_{20}$ with a thickness of 15 nm,
- 5 - a transparent silver layer 6 with a thickness of 15 nm,
- a further dielectric layer 7 of AlN with a thickness of 220 nm;

a spacer layer 8 of a UV-cured acrylate with a thickness of 50 μm ;

a second recording stack 9 with an IPIM structure comprising:

- a dielectric layer 10 of $(\text{ZnS})_{80}(\text{SiO}_2)_{20}$ with a thickness of 190 nm,
- 10 - a recording layer 11 of the compound GeSb_2Te_4 with a thickness of 25 nm,
- a dielectric layer 12 of $(\text{ZnS})_{80}(\text{SiO}_2)_{20}$ with a thickness of 15 nm,
- an aluminium mirror layer 13 with a thickness of 100 nm.

The initial crystalline state of the recording layers 4 and 11 is obtained by heating the as-deposited amorphous alloy with a focused laser beam in a recorder.

15 A laser-light beam 14 for recording, reproducing and erasing of information is focused onto recording stack 2, and enters the stack 2 via the substrate 1. Laser-light beam 15 is focused onto recording layer 11 of the second recording stack 9.


The first recording stack has a transmission in the amorphous state of about 50%, and a transmission in the crystalline state of about 33%. The stack has good recording properties. The jitter is below 13% up to 4000 overwrite cycles.

20 According to the invention a rewritable single-sided double layer phase change optical information medium is provided, such as DVD-RAM or DVR, in which the storage capacity is doubled with respect to a single-layered recording medium.

CLAIMS:

1. An optical information medium for rewritable double layer recording by means of a laser-light beam, said medium comprising a substrate having disposed on the same side thereof in this order:
 - a first recording stack comprising a phase change type recording layer sandwiched between
5 two dielectric layers, and a transparent metal layer and a further dielectric layer on the side opposite the side of the first recording stack on which the laser-light beam is incident;
 - a transparent spacer layer having a thickness larger than the depth of focus of the laser-light beam; and
 - a second recording stack comprising a phase change type recording layer sandwiched
10 between two dielectric layers, and a metal mirror layer on the side opposite to the side of the second recording stack on which the laser-light beam is incident.
2. An optical information medium as claimed in Claim 1, characterized in that the
15 metal layer of the first recording stack has a thickness between 10 and 30 nm.
3. An optical information medium as claimed in Claim 1, characterized in that the
metal layer of the first recording stack comprises silver.
4. An optical information medium as claimed in Claim 1, characterized in that the
20 spacer layer has a thickness of at least 10 μm .
5. An optical information medium as claimed in Claim 1, characterized in that the
recording layers comprise a GeSbTe compound.
- 25 6. An optical information medium as claimed in Claim 1, characterized in that the
further dielectric layer comprises a compound selected from the group consisting of Al_2O_3 ,
 SiC , Si_3N_4 , MgO , ZnO and AlN including their non-stoichiometric compositions.

1/1





INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : G11B 7/24		A3	(11) International Publication Number: WO 99/59143
			(43) International Publication Date: 18 November 1999 (18.11.99)
(21) International Application Number: PCT/IB99/00840		(81) Designated States: JP, KR, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 10 May 1999 (10.05.99)			
(30) Priority Data: 98201552.1 12 May 1998 (12.05.98) EP		Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.	
(71) Applicant: KONINKLIJKE PHILIPS ELECTRONICS N.V. [NL/NL]; Groenewoudseweg 1, NL-5621 BA Eindhoven (NL).		(88) Date of publication of the international search report: 6 January 2000 (06.01.00)	
(71) Applicant (for SE only): PHILIPS AB [SE/SE]; Kottbygatan 7, Kista, S-164 85 Stockholm (SE).			
(72) Inventors: WIERENGA, Harm, A.; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). RIJPERS, Johannes, C., N.; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).			
(74) Agent: STOLK, Steven, A.; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).			
(54) Title: REWRITABLE OPTICAL INFORMATION MEDIUM			
(57) Abstract <p>A description is given of a rewritable single-sided double layer optical information medium having a first recording stack (2) with a phase change recording layer (4) sandwiched between two dielectric layers (3, 5). The recording stack (2) is sufficiently transmissive to ensure proper reading/writing of the second recording stack (9). For this purpose, the recording stack (2) comprises a thin metal layer (6) and a further dielectric layer (7). The laser beam (14, 15) can be focused on the first recording stack (2) or on the second recording stack (9), thus doubling the storage capacity of the recording medium.</p>			
<p>The diagram illustrates a cross-section of the optical medium. It consists of a substrate with two recording stacks. The first recording stack (2) is located in the upper part of the substrate and includes layers 3, 4, 5, 6, and 7. The second recording stack (9) is located below the first stack and includes layers 10, 11, 12, and 13. Two laser beams, labeled 14 and 15, are shown as cones of light focusing on the first and second recording stacks respectively. The layers are numbered 1 through 15, with 1 being the top surface of the substrate and 15 being the bottom surface of the second stack.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

INTERNATIONAL SEARCH REPORT

International application No.

PCT/IB 99/00840

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: G11B 7/24

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: G11B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5192626 A (MASAHIKO SEKIYA ET AL), 9 March 1993 (09.03.93) --	1-6
A	US 5485452 A (TAKANORI MAEDA), 16 January 1996 (16.01.96) --	1-6
A	US 5627816 A (NOBORU ITO ET AL), 6 May 1997 (06.05.97) --	1-6
A	WO 9631875 A2 (MATSUSHITA ELECTRIC INDUSTRIAL CO.), 10 October 1996 (10.10.96) --	1-6



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"I" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"I" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

16 November 1999

Date of mailing of the international search report

18-11-1999

Name and mailing address of the ISA/

Swedish Patent Office

Box 5055, S-102 42 STOCKHOLM

Facsimile No. +46 8 666 02 86

Authorized officer

Benny Andersson/mj

Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

International application No.

PCT/IB 99/00840

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>EP 0566107 A1 (MATUSHITA ELECTRIC INDUSTRIAL CO.), 20 October 1993 (20.10.93)</p> <p style="text-align: center;">-- -----</p>	1-6

INTERNATIONAL SEARCH REPORT

Information on patent family members

02/11/99

International application No.

PCT/IB 99/00840

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5192626 A	09/03/93	CA 2004936 A,C DE 68921308 D,T EP 0373539 A,B JP 2523180 B JP 3005929 A JP 2062004 C JP 2161629 A JP 7099596 B JP 2177035 A JP 2528173 B	14/06/90 28/09/95 20/06/90 07/08/96 11/01/91 10/06/96 21/06/90 25/10/95 10/07/90 28/08/96
US 5485452 A	16/01/96	EP 0520619 A JP 5006571 A	30/12/92 14/01/93
US 5627816 A	06/05/97	JP 7078353 A US 5563873 A US 5768251 A	20/03/95 08/10/96 16/06/98
WO 9631875 A2	10/10/96	CN 1157048 A EP 0764323 A JP 10505188 T US 5764619 A	13/08/97 26/03/97 19/05/98 09/06/98
EP 0566107 A1	20/10/93	DE 69317459 D,T JP 5298747 A US 5424106 A US 5545454 A JP 5298748 A JP 6004903 A	27/08/98 12/11/93 13/06/95 13/08/96 12/11/93 14/01/94